

Technical Bulletin



<u>APPLICATION:</u>	Brush, roll, aerosol, spray conventional or airless. When using spray equipment, use a 17- tip opening. DO NOT THIN!
<u>SALT SPRAY RESISTANCE:</u>	300 hours as per ASTM B 117, with a 3 mil (0.003 inches) dry film thickness.
<u>ACCELERATED WEATHERING:</u>	500 hours as per ASTM E 42, with various topcoats.
<u>ADHESION TEST:</u>	25 square cross hatch test; no loss in inter-coat adhesion nor in overall adhesion to the rusted surface after 300 hours of salt spray ASTM B 117, and 500 hours of accelerated weathering ASTM E 42 using top coats of solvent base epoxy, 2 component polyurethanes, or exterior alkyd enamels.
<u>X-RAY DIFFRACTION:</u>	Product changes from active to passive stage.
<u>METALLOGRAPHY TEST:</u>	Product fills all open areas of corrosion, surrounds all loose portions and produces an unbroken protective layer.
<u>FLEXIBILITY:</u>	No cracking when bent over 1/4" mandrel through 180°
<u>SOLVENT EMISSION:</u>	Meets rule 66 and EPA requirements.
<u>COVERAGE:</u>	300 square feet per gallon with a 3 mil (0.003 inches) dry film thickness, depending on the roughness and porosity of the surface, and method of application.
<u>COMPOSITION:</u>	Oleo-resinous resin with chemically active ingredients.
<u>VISCOSITY:</u>	86-92 KU
<u>WEIGHT PER GALLON:</u>	10.5 LBS. Minimum.
<u>TOTAL SOLIDS:</u>	59% minimum per weight of paint.
<u>*DRYING TIME:</u>	6 hours maximum to touch.
<u>THROUGH DRY:</u>	24 hours.
<u>TO TOPCOAT:</u>	24 to 72 hours, depending on environmental conditions.
<u>SOLVENT:</u>	Aliphatic.
<u>VOC:</u>	250 G/L ASTM D 396.
<u>FLASH POINT:</u>	106°F (41.11°C)
<u>GRIND:</u>	5 minimum.
<u>PIGMENT:</u>	Does NOT contain lead, chrome or other toxic pigments.
<u>CORROSION DEPOSITS:</u>	Results of salt spray test ASTM B 117, and accelerated weathering test ASTM E 42 will prove there could be no evidence of corrosion.
<u>*DRYING. CURING TIME:</u>	At 77°F (25°C) at 50% humidity with a 3 mil (0.003 inches) dry film thickness.
<u>**TOPCOAT:</u>	When using topcoats containing aliphatic solvents such as mineral spirits, allow RUST DESTROYER ® to cure for 24 hours. In lower temperature or higher humidity than shown above allow 36 hours to cure before top coating. When using top coats containing Aromatic solvents, Esters or Ketones or Latex allow 72 hours to cure before top coating. Always spot test a small area for proper cure time.